

Technical Datasheet ABS-50

1) Product Description:

2) Applications:

Electronic and Electrical parts, vacuum cleaner, washing machine cover and Refrigerator door cap & etc.

3) Typical data:

Property	Test method (ASTM)	Test condition	Unit	Typical value	ABS-50 Specification
Izod Impact	D- 256	6.4 mm , notched	Kj/m ²	23	Min19
Melt flow index	D-1238	220°C , 10 kg	gr/10 min	35	29-39
Rock well hardness	D-785	R-scale	109	95-115
HDT	D-648	1.82 m pa	°C	85	Min82
Vicat softening Temp	D-1525	5kg/50°C	°C	95	Min 93
Tensile strength	D-638	23°C , 50 mm/min	Kg/cm ²	455	Min 420
Tensile elongation	D-638	23°C , 50 mm/min	%	20	Min 16
Flexural strength	D-790	23°C , 2.8 mm/min	Kg/cm ²	650	Min 620
Flexural Modulus	D-790	23°C , 2.8 mm/min	Kg/cm ²	22000	Min 17000
Specific Gravity	D-792	23°C	..	1.04	1.04
Molding Shrinkage	D-955	...	%	0.4-0.7	0.4-0.7
Flammability	U194	1/8inch(3.2mm)	...	HB	HB

* Typical values not to be construed as specifications.